



Ultrapure® High Reliability Extruded Bar Solder

Lead-bearing and Lead-free alloys

Product Description

For soldering applications which require maximum reliability of solder joints, especially for surface mounted components, only solder of the highest purity is acceptable. Kester does not make any vague claims of outstanding solder purity. Complete analysis of Kester Ultrapure® Bar Solders prove that every batch conforms to the strictest quality control standards in the solder industry.

Maximum Allowed Impurities

Kester Ultrapure® Bar Solder meets the requirements of current industry standards for allowable impurity requirements. Elements are considered impurities if they are not listed as components in the composition of the alloy.

Element	Symbol	J-STD-006C	Kester Ultrapure®
Tin	Sn	0.25	0.2500
Lead	Pb	0.07	0.0700
Antimony	Sb	0.20	0.2000
Copper	Cu	0.08	0.0800
Gold	Au	0.05	0.0500
Aluminum	Al	0.005	0.0050
Cadmium	Cd	0.002	0.0020
Zinc	Zn	0.003	0.0030
Silver	Ag	0.10	0.1000
Bismuth	Bi	0.10	0.1000
Arsenic	As	0.03	0.0300
Iron	Fe	0.02	0.0200
Indium	In	0.10	0.1000
Nickel	Ni	0.01	0.0100

Kester Ultrapure® will conform to these requirements when purchased directly or through stocking distributors. Kester is the only manufacturer of Ultrapure® quality solder. Kester Ultrapure® conforms to the requirements of J-STD-006C. DOD-STD-2000-1A (Soldering Technology, High Quality/High Reliability) states that it is the responsibility of the manufacturer to select those materials and processes that will produce acceptable high quality/high reliability products.

Available Alloys

	Melting Point
Lead-bearing	
Sn63Pb37	183°C (361°F)
Sn60Pb40	183-190°C (361-374°F)
Lead-free	
K100LD	~227°C (441°F)
Sn96.5Ag3.5	221°C (430°F)
Sn96.5Ag3.0Cu0.5	217-220°C (423-428°F)
Sn99.3Cu0.7	227°C (441°F)
Sn100	232°C (450°F)

Storage and Shelf Life:

Kester Ultrapure® solder has no limited shelf life when handled properly. Storage must be in a dry, non-corrosive environment. The solder surface may lose its shine and appear a dull shade of gray. This is a surface phenomenon and is not detrimental to product functionality.

Health & Safety:

This product, during handling or use, may be hazardous to health or the environment. Read the Material Safety Data Sheet and warning label before using this product.

World Headquarters: 800 West Thorndale Avenue, Itasca, Illinois, 60143 USA

Phone: (+1) 630-616-4000 • **Email:** customerservice@kester.com • **Website:** www.kester.com

Asia Pacific Headquarters

500 Chai Chee Lane
Singapore 469024
(+65) 6449-1133
customerservice@kester.com.sg

European Headquarters

Zum Plom 5
08541 Neuensalz
Germany
(+49) 3741 4233-0
customerservice@kester-eu.com

Japanese Headquarters

20-11 Yokokawa 2-Chome
Sumida-Ku
Tokyo 130-0003 Japan
(+81) 3-3624-5351
jpsales@kester.com.sg
